


## FPDS-O

波纹管


Corrugated conduit

+110°C  
-50°C



+230°F  
-58°F

Material: PA12 MOD BS 橙色/orange  
色号 RAL2003 / similar to RAL2003



- 用于特殊线缆束的标记
  - 自熄, 不含卤素和镉
  - 优异的动态抗疲劳性能
  - 优异的耐化学品性能
  - 优异的耐候性能
- or marking special wiring
  - self-extinguishing, free of halogen and cadmium
  - good dynamic fatigue strength
  - very good chemical resistance
  - good weathering performances

温度范围 / Temperature range  
弯曲性能 / 柔韧性 / Flexibility/Ductility  
动态性能 / Dynamic  
机械防护性能 / Mechanical protection  
防火性能 / Fire precaution performance  
耐化学品性能 / Chemical resistance  
耐候性 / Resistance to weathering

min.		max.	
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■



产品号 Part No. <sup>1)</sup>	名义尺寸 Nominal width		接头系统 Fitting system	波型 Profile <sup>2)</sup>	尺寸 Dimensions in mm (nom.) <sup>3)</sup>		弯曲半径 Bending radius in mm		包装单元 PU m
	NW	metr.			内径 / ID	外径 / OD	stat. R.	dyn. R.	
橙色 RAL2003 / similar to RAL2003									
FPDSF-0702.50	7	10	FIPLOCK® ONE	F	6,2	10,0	15	40	50
FPDSF-1002.50	10	12		F	9,6	12,8	20	45	50
FPDSF-1202.50	12	16		F	12,0	15,7	25	55	50
FPDSF-1702.50	17	20		F	16,6	21,1	30	65	50
FPDSF-2302.50	23	25		F	22,6	27,9	35	80	50
FPDSF-2902.50	29	32		F	29,0	33,8	45	100	50
FPDSF-3602.25	36	40		F	36,5	42,2	60	155	25
FPDSF-4802.25	48	50		F	47,5	54,0	70	170	25
FPDSC-1702.50	17	20		C	16,1	21,1	30	75	50
FPDSC-2302.50	23	25		C	22,0	28,3	40	90	50
FPDSC-2902.50	29	32	C	28,3	34,4	50	110	50	
FPDSC-3602.25	36	40	C	36,6	42,2	55	170	25	
FPDSC-4802.25	48	50	C	47,0	54,0	65	190	25	
FPDSC-5602.25	56	68	C	56,3	67,2	100	250	25	
FPDSC-7002.25	70	80	C	67,2	79,6	135	320	25	
FPDSC-9502.10	95	106	C	91,3	106,0	150	420	10	
FPDSC-12502.10	125	146	C	126,5	146,5	320	460	10	

您可以通过以下地址查询更多的技术信息 / You can find more technical information here

CADENAS – 产品CAD数据目录 / eCATALOGsolutions electronic CAD catalog: <https://fraenkische-ip.partcommunity.com>

<sup>1)</sup> FIPLOCK® 波纹管编码规则 / Part numbering key for FIPLOCK® corrugated conduits: [www.fraenkische-ip.com/fiplock-part-no](http://www.fraenkische-ip.com/fiplock-part-no)

<sup>2)</sup> 波纹管波型 / Conduit profiles: [www.fraenkische-ip.com/fipsystems-profiles](http://www.fraenkische-ip.com/fipsystems-profiles)

<sup>3)</sup> 英制尺寸转换 / Conversion to inch: [www.fraenkische-ip.com/fipsystems-conversion-inch](http://www.fraenkische-ip.com/fipsystems-conversion-inch)

产品认证报告基于 FPDSF NW 07–48 及 FPDSF NW 17–48 连接 FIPLOCK® ONE 管接头。

Recognised Component certification is valid for FPDSF NW 07–48 and FPDSC NW 17–48 in connection with FIPLOCK® ONE fittings.



# FPDS-O 产品性能 / Product performances

应用性能 Application performances	特性 Characteristics	单位 Unit	规范标准 Standards, specifications	备注 Remark
温度范围 / Temperature range	-50 到 / to +110 -58 到 / to +230	°C °F	IS FIP	
温度 (短周期) / Temperature (short-term)	150 (500 h); 165 (100 h) 302 (500 h); 329 (100 h)	°C °F	IS FIP	
填充率 (最大) / Filling ratio (max.)	70	%	IS FIP	推荐值 / Recommendation

机械性能 / Mechanical performances				
冲击强度 / Impact strength	6	J	IS FIP	23°C / 73,4°F
冲击强度 / Impact strength	1	J	IS FIP	-45°C / - 49°F
冲击强度 / Impact strength	1J/2J	Joule	FIP-ISTR-1601	-50°C / - 58°F
峰值负载 / Peak load value	125	N	依照 IEC EN 61386 according to IEC EN 61386	
拔脱强度 / Pull out strength	250	N	依照 IEC EN 61386 according to IEC EN 61386	23°C / 73,4°F FIPLOCK ONE NW 17

防火性能 / Fire safety performances				
不含卤素和镉 / Free from halogens and cadmium	是 / yes		DIN EN ISO 63355:2023-08	
阻燃等级 / Fire classification	V2		UL 94	
氧指数 / Oxygen index	32	%	EN ISO 4589-2	
灼热丝测试 / Glow wire test	850 / 1562	°C / °F	IEC 60695	
火灾危害等级 / Fire hazardous level	HL2 R22 / HL3 R23		EN45545-2	
火焰蔓延 / Spread of fire	非火焰蔓延 non flame propagating		IEC EN 61386	
垂直燃烧测试 / Vertical burning behavior	Vi<100 自熄 Vi<100 self-extinguishing	mm/min	EN ISO 6941:2003	ECE R-118-02 附录 8 ECE R-118-02 annex 8

耐候性 / Weathering performances				
UV- 及耐候性能 UV and weathering performance	优异 excellent		IS FIP	可达 20 年 up to 20 years

测试条件参照EN ISO 139 , 温度 23°C / 湿度50% r. F. (如未注明测试条件). IS FIP = FIP内部测试规范  
Tests carried out acc. EN ISO 139 at 23°C / 50% r. h. (if not indicated differently). IS FIP = Internal Specification FIP

我们尽我们的知识水平所提供的数据, 图片和技术规格图档反映了当前的工程技术水平。这并不包含对最后应用有关的任何责任。产品用户需根据应用要求自行进行评估。以确定产品是否符合特殊应用条件。我们对产品的责任只考虑一般规定条件下的水平。FIP保留对产品数据和数值进行技术调整的权利。例如更改材料和加工工艺, 在保证产品性能数值不下降的情况下不会另行通知。

The provided data, images and technical specification drawings reflect the current engineering level and are to the best of our knowledge. This does not include any liability regarding the final application. Users of the products have to make their own evaluation to determine the suitability for a specific application. Our liability for these products considers the stated level within our General Conditions only. FRAENKISCHE Industrial Pipes (FIP) reserves the right to adjust specified data and values as well as implementing technical adjustments of the products e. g. change of materials and processing technologies without prior notice as long as the specified values are not reduced.